



## Technical Data Sheet

### LOWSET ME10

<b>Appearance</b>	<b>White powder</b>
<b>Colour</b>	<b>White- pale yellow</b>
<b>pH at 20° C (10% wt solution)</b>	<b>8.5 ± 1</b>
<b>Bulk density (g/ml)</b>	<b>0.70 ± 0.10</b>
<b>Behaviour in water</b>	<b>soluble</b>
<b>Dry matter (% wt)</b>	<b>≥ 96.0</b>
<b>Process</b>	<b>Condensation of sulfonated melamine and formaldehyde</b>
<b>Ionic charge</b>	<b>Anionic</b>
<b>Chemical composition</b>	<b>Sulphitated melamine-formaldehyde resin</b>
<b>Recommended working concentration</b>	<b>From 0.4 to 2 kg / 100 kg of cement</b>
<b>Compatibility</b>	<b>Not compatible with additives as ligno-sulphonate, gluconate, anti-shrink products</b>
<b>Storage temperature (°C)</b>	<b>5 - 25</b>
<b>Shelf life (months)</b>	<b>24</b>

The data in this Technical Data Sheet is provided for information only. It is correct to the best of our knowledge, information and belief at the date of its publication. It does not constitute a specification and no liability is assumed, nor freedom from any existing patents.

Print date : 01/05/2018